

TECHNICAL DATA SHEET FLUTING WB

Quality Parameters	Standard	FLUTING								
Grammage g/m ²	ISO 536	90	100	110	115	120	125	130	140	150
Tolerance individual%	ISO 536	±4								
Tolerance average%		±2								
CMT30 N typical	ISO 7263	145	160	180	190	200	205	215	225	235
CMT30 N minimum		135	150	170	180	190	195	205	215	225
SCT KN/m typical	ISO 9895	1,50	1,60	1,84	1,90	2,00	2,05	2,15	2,25	2,35
SCT KN/m minimum		1,35	1,50	1,70	1,80	1,90	1,95	2,05	2,15	2,25
Moisture %	ISO 287	6-9								

All values refer to a standard atmosphere 23°C, 51% relative humidity

Quality Manager
Tatjana Mladenović




Fabrika hartije Beograd d.o.o.
Beograd

Prilazni put Ada Huji br. 9,
11060 Beograd, Srbija

Tel: +381 11 3316501

Fax: +381 11 2771322

www.fabrikahartije.rs

Email: info@fabrikahartije.rs

PIB: 102350996

MB: 07006497