

**TECHNICAL DATA SHEET
SCHRENZ**

Quality Parameters	Standard	SCHRENZ							
Grammage g/m ²	ISO 536	90	100	110	120	140	180	200	230
Tolerance individual%	ISO 536	±4							
Tolerance average%		±2							
Bursting strenght kPa	ISO 2758	140	150	165	180	200	270	300	345
Moisture %	ISO287	6-9							

All values refer to a standard atmosphere 23°C, 51% relative humidity



Quality Manager
Tatjana Mladenović



Fabrika hartije Beograd d.o.o.
Beograd

Prilazni put Ada Huji br. 9,
11060 Beograd, Srbija

Tel: +381 11 3316501

Fax: +381 11 2771322

www.fabrikahartije.rs

Email: info@fabrikahartije.rs

PIB: 102350996

MB: 07006497