

TECHNICAL DATA SHEET TESTLINER 3

Quality Parameters	Standard	TESTLINER 3								
Grammage g/m ²	ISO 536	100	110	115	120	125	135	140	170	200
Tolerance individual%	ISO 536	±4								
Tolerance average%		±2								
Bursting strenght KPa typical	ISO 2758	260	280	290	300	310	335	360	430	490
Bursting strenght KPa minimum		220	240	250	265	275	290	305	375	440
SCT test CD KN/m typical	ISO 9895	1,55	1,70	1,78	1,86	1,93	2,09	2,17	2,63	3,10
SCT test CD KN/m minimum		1,40	1,54	1,61	1,68	1,75	1,89	1,96	2,38	2,80
Bond test mJ min	SRPS H.N8 217	95								
Cobb test 60sec g H ₂ O/m ²	ISO 535	20-40								
Moisture %	ISO287	6-9								

All values refer to a standard atmosphere 23°C, 51% relative humidity


Quality Manager
Tatjana Mladenović
Tatjana Mladenović

Fabrika hartije Beograd d.o.o.
Beograd

Prilazni put Ada Huji br. 9,
11060 Beograd, Srbija

Tel: +381 11 3316501

Fax: +381 11 2771322

www.fabrikahartije.rs

Email: info@fabrikahartije.rs

PIB: 102350996

MB: 07006497