

# Šrenc / Schrenz

## Informacije o proizvodu / General description

Šrenc predstavlja još jednu vrstu linera, koji se koristi uglavnom za unutrašnji ravni sloj troslojne kutije ili kod petoslojne kutije za izradu srednjeg i unutrašnjeg ravnog sloja.

Obzirom da se papir izrađuje bez dodavanja skroba, boje i tutkala, kakav je slučaj kod Testlanera, radi se o papiru sa nižim tehničkim karakteristikama od Testlanera.

Svoju primenu može naći i u izradi papirnih hilzni male nosivosti, pre svega u proizvodnji higijenskih papira.

Schrenz is another liner, used mostly for the inner layer of a triple-layered box or a five-layer box for the middle and inner layer.

Considering the fact that this paper is made without the addition of starch, color or glue, which is the case with Testliner, this paper has lower technical characteristics than Testliner.

It can be used also for making paper cores of small load-bearing capacity, mostly in the production of toilet paper.

## Tehnički podaci / Technical information

Svojstva/Properties	Jedinica/Unit Standard			Zadate vrednosti / Target figures								
Gramatura / Grammage	g/m <sup>2</sup>	ISO 536	90	100	110	120	125	130	140	180	200	230
Vlaga / Moisture	%	ISO 287	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5
Mullen / Bursting Strenght Min	kPa	ISO 2758	140	150	165	180	187	195	200	270	300	345

## Odstupanje / Tolerance

Svojstva/Properties	Jedinica/Unit Standard		Odstupanje / Tolerance
Pojedinačna Gramatura / Individual Grammage	g/m <sup>2</sup>	ISO 536	± 4%
Prosečna Gramatura / Average Grammage	g/m <sup>2</sup>	ISO 536	± 2%
Vlaga / Moisture	%	ISO 287	± 1,5%

Uslovi ispitivanja / Test condition ISO 187

**23°C ±1°C, 50% ±2% RH**

Važi od / Valid from  
**April / April 2019**

Direktor upravljanja kvalitetom i ekologijom /  
Director of quality control and ecology  
**Tatjana Mladenović**